

NHG低熔点玻璃模压前后谱线折射率对照参考值

牌号	分类	nA'	nr	nC	nC'	nHe-Ne	nD	nd	ne	nF	nF'	ng	nh	ni
		768.19	706.52	656.27	643.85	632.8	589.29	587.56	546.07	486.13	479.99	435.84	404.66	365.01
D-FK61	模压前	1.49301	1.49407	1.49514	1.49543	1.49571	1.49694	1.49700	1.49845	1.50123	1.50157	1.50451	1.50721	1.51173
	模压后	1.49184	1.49290	1.49397	1.49426	1.49454	1.49577	1.49581	1.49726	1.50005	1.50039	1.50331	1.50601	1.51053
D-FK90	模压前	1.45524	1.45615	1.45704	1.45729	1.45752	1.45855	1.45860	1.45981	1.46212	1.46241	1.46486	1.46710	1.47085
	模压后	1.45429	1.45520	1.45609	1.45633	1.45656	1.45759	1.45764	1.45885	1.46116	1.46145	1.46388	1.46612	1.46987
D-FK95	模压前	1.43396	1.43478	1.43559	1.43582	1.43603	1.43696	1.43700	1.43810	1.44019	1.44044	1.44264	1.44466	1.44803
	模压后	1.43317	1.43399	1.43480	1.43503	1.43524	1.43617	1.43620	1.43730	1.43941	1.43966	1.44184	1.44386	1.44723
D-K9	模压前	1.51094	1.51241	1.51384	1.51424	1.51461	1.51625	1.51633	1.51825	1.52190	1.52236	1.52621	1.52976	1.53574
	模压后	1.50975	1.51122	1.51265	1.51305	1.51342	1.51506	1.51511	1.51703	1.52069	1.52115	1.52503	1.52858	1.53456
D-PK60	模压前	1.58618	1.58775	1.58931	1.58974	1.59014	1.59193	1.59201	1.59412	1.59814	1.59864	1.60291	1.60684	1.61349
	模压后	1.58401	1.58558	1.58714	1.58757	1.58797	1.58976	1.58982	1.59193	1.59596	1.59646	1.60073	1.60466	1.61131
D-PK62	模压前	1.61249	1.61418	1.61586	1.61633	1.61676	1.61872	1.61881	1.62112	1.62555	1.62610	1.63084	1.63522	1.64265
	模压后	1.61047	1.61216	1.61384	1.61431	1.61474	1.61670	1.61681	1.61912	1.62355	1.62410	1.62882	1.63320	1.64063
D-PK70	模压前	1.51999	1.52136	1.52269	1.52306	1.52341	1.52493	1.52500	1.52679	1.53017	1.53058	1.53413	1.53738	1.54287
	模压后	1.51627	1.51764	1.51897	1.51932	1.51967	1.52119	1.52126	1.52303	1.52638	1.52679	1.53034	1.53359	1.53908
D-ZK2N	模压前	1.58054	1.58228	1.58399	1.58448	1.58492	1.58691	1.58700	1.58935	1.59384	1.59441	1.59918	1.60364	1.61145
	模压后	1.57867	1.58040	1.58212	1.58259	1.58304	1.58504	1.58512	1.58747	1.59196	1.59251	1.59731	1.60177	1.60959
D-ZK3L	模压前	1.58275	1.58448	1.58618	1.58665	1.58709	1.58904	1.58913	1.59142	1.59580	1.59634	1.60095	1.60520	1.61247
	模压后	1.58068	1.58241	1.58412	1.58459	1.58503	1.58699	1.58706	1.58935	1.59373	1.59427	1.59890	1.60317	1.61040
D-ZK50	模压前	1.60194	1.60380	1.60565	1.60616	1.60664	1.60876	1.60886	1.61136	1.61616	1.61676	1.62184	1.62655	1.63460
	模压后	1.59974	1.60160	1.60345	1.60396	1.60444	1.60656	1.60666	1.60916	1.61395	1.61455	1.61965	1.62436	1.63241
D-LaK6	模压前	1.68506	1.68731	1.68955	1.69017	1.69076	1.69338	1.69350	1.69661	1.70258	1.70333	1.70973	1.71570	1.72593
	模压后	1.68233	1.68460	1.68686	1.68748	1.68807	1.69069	1.69081	1.69392	1.69988	1.70063	1.70704	1.71302	1.72323

牌号	分类	nA'	nr	nC	nC'	nHe-Ne	nD	nd	ne	nF	nF'	ng	nh	ni
		768.19	706.52	656.27	643.85	632.8	589.29	587.56	546.07	486.13	479.99	435.84	404.66	365.01
D-ZF10	模压前	1.67552	1.67896	1.68249	1.68350	1.68445	1.68875	1.68893	1.69417	1.70466	1.70600	1.71785	1.72959	1.75178
	模压后	1.67119	1.67463	1.67816	1.67917	1.68012	1.68442	1.68453	1.68977	1.70003	1.70137	1.71322	1.72496	1.74715
D-ZF52N	模压前	1.82565	1.83096	1.83648	1.83806	1.83955	1.84635	1.84666	1.85504	1.87209	1.87431	1.89430	1.91469	1.95467
	模压后	1.82050	1.82578	1.83124	1.83280	1.83426	1.84096	1.84126	1.84954	1.86638	1.86856	1.88829	1.90844	1.94807
D-LaF050	模压前	1.75802	1.76066	1.76331	1.76406	1.76475	1.76787	1.76802	1.77173	1.77891	1.77980	1.78753	1.79475	1.80718
	模压后	1.75522	1.75786	1.76051	1.76122	1.76191	1.76503	1.76518	1.76888	1.77604	1.77693	1.78466	1.79188	1.80431
D-LaF50	模压前	1.76248	1.76513	1.76779	1.76854	1.76923	1.77236	1.77250	1.77622	1.78340	1.78430	1.79204	1.79927	1.81174
	模压后	1.75963	1.76228	1.76494	1.76568	1.76637	1.76950	1.76962	1.77335	1.78053	1.78144	1.78918	1.79641	1.80888
D-LaF731	模压前	1.71949	1.72243	1.72541	1.72625	1.72705	1.73061	1.73077	1.73505	1.74345	1.74452	1.75376	1.76260	1.77835
	模压后	1.71738	1.72033	1.72331	1.72415	1.72494	1.72851	1.72871	1.73299	1.74133	1.74240	1.75159	1.76042	1.77618
D-LaF743	模压前	1.73366	1.73621	1.73876	1.73948	1.74016	1.74317	1.74330	1.74689	1.75383	1.75470	1.76215	1.76911	1.78110
	模压后	1.73097	1.73353	1.73608	1.73680	1.73748	1.74049	1.74060	1.74419	1.75111	1.75198	1.75946	1.76642	1.77841
D-ZLaF52L	模压前	1.79371	1.79694	1.80022	1.80114	1.80201	1.80592	1.80610	1.81080	1.82002	1.82117	1.83126	1.84085	1.85784
	模压后	1.79105	1.79427	1.79754	1.79846	1.79934	1.80326	1.80344	1.80814	1.81729	1.81844	1.82853	1.83812	1.85508
D-ZLaF52N	模压前	1.79762	1.80084	1.80411	1.80505	1.80591	1.80982	1.81000	1.81469	1.82387	1.82502	1.83508	1.84465	1.86160
	模压后	1.79494	1.79816	1.80143	1.80237	1.80322	1.80714	1.80734	1.81203	1.82114	1.82229	1.83237	1.84193	1.85887
D-ZLaF52N-M170	模压前	1.79599	1.79921	1.80247	1.80340	1.80427	1.80817	1.80834	1.81303	1.82223	1.82339	1.83343	1.84298	1.85982
	模压后	1.79331	1.79653	1.79979	1.80072	1.80159	1.80549	1.80568	1.81037	1.81950	1.82066	1.83070	1.84025	1.85709
D-ZLaF53	模压前	1.82054	1.82414	1.82781	1.82884	1.82981	1.83421	1.83441	1.83972	1.85019	1.85152	1.86316	1.87437	1.89451
	模压后	1.81699	1.82060	1.82428	1.82531	1.82629	1.83069	1.83088	1.83619	1.84661	1.84794	1.85958	1.87080	1.89094
D-ZLaF814	模压前	1.80110	1.80465	1.80825	1.80927	1.81023	1.81455	1.81474	1.81995	1.83025	1.83156	1.84293	1.85388	1.87363
	模压后	1.79769	1.80124	1.80484	1.80581	1.80677	1.81109	1.81128	1.81642	1.82672	1.82800	1.83937	1.85032	1.87007
D-ZLaF851	模压前	1.83808	1.84154	1.84505	1.84604	1.84697	1.85116	1.85135	1.85639	1.86628	1.86753	1.87838	1.88871	1.90699
	模压后	1.83525	1.83871	1.84222	1.84321	1.84414	1.84833	1.84849	1.85353	1.86340	1.86465	1.87549	1.88582	1.90410